
Paints and varnishes — Determination of solar reflectance

Peintures et vernis — Détermination de réflexion solaire

STANDARDSISO.COM : Click to view the full PDF of ISO 22969:2019



STANDARDSISO.COM : Click to view the full PDF of ISO 22969:2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	2
4.1 Spectrophotometer	2
5 Procedure	2
5.1 Spectral reflectance of test specimen.....	2
5.2 Reference global solar radiation.....	2
5.3 Determination of solar reflectance.....	3
6 Test report	3
Annex A (informative) The reference global radiation table	4
Annex B (informative) Example of a determination method of solar reflectance	8
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The solar reflectance property of a coating system is determined by the absorbed solar energy (especially heat) of a building or an object.

This property can be expressed by a numerical value determined by calculation, thanks to which the impact of solar energy (especially heat) on the environment can be easily understood.

Reduction of greenhouse gases and carbon dioxide (CO₂) is achieved by reflecting the solar energy back into the atmosphere, which, reduces global warming. The effect of energy saving by coating system can be determined using solar reflectance.

STANDARDSISO.COM : Click to view the full PDF of ISO 22969:2019

STANDARDSISO.COM : Click to view the full PDF of ISO 22969:2019

Paints and varnishes — Determination of solar reflectance

1 Scope

This document specifies a method to determine the solar reflectance of coating systems using a spectrophotometer with a wide spectral range (300 nm to 2 500 nm) and global solar radiation.

This document is applicable to coating systems.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 4618, *Paints and varnishes — Terms and definitions*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

global solar radiation

total of the direct solar radiation incident on a horizontal surface plus all sky and horizontal ground reflected radiation within the 2π steradian field of view of the surface

Note 1 to entry: It is expressed in watts per square metre ($\text{W}\cdot\text{m}^{-2}$).

3.2

radiant flux

radiant power

power emitted, transmitted or received in the form of radiation

Note 1 to entry: It is expressed in watts (W).

[SOURCE: IEC 60050-845:1987, 845-01-24]

3.3

reflectance

ρ

ratio of the reflected radiant or luminous flux to the incident flux in the given spectral composition, polarization and geometrical distribution

[SOURCE: IEC 60050-845:1987, 845-04-58]

3.4

solar reflectance

SR

total solar reflectance

TSR

solar reflectance index

SRI

ratio of reflected radiant flux to *global solar radiation* (3.1) on coating system

3.5

integrating sphere

hollow sphere whose internal surface is a diffuse reflector, as non-selective as possible

Note 1 to entry: An integrating sphere is frequently used with a radiometer or photometer.

[SOURCE: IEC 60050-845:1987, 845-05-24]

3.6

spectrophotometer

instrument for measuring the ratio of two values of a radiometric quantity at the same wavelength

[SOURCE: IEC 60050-845:1987, 845-05-08]

4 Apparatus

4.1 Spectrophotometer

Spectrophotometer with a spectrometer capable of collecting radiations from 300 nm to 2 500 nm utilizing an integrating sphere with either 8°:di or di:8° geometry so that the regular or specular reflection may be included. See CIE 15 for details.

5 Procedure

5.1 Spectral reflectance of test specimen

Measurement of spectral reflectance of test specimens shall use the apparatus described in [Clause 4](#) and the scale used for reflectometers shall be traceable to national metrology institutions. Unless otherwise specified, spectral reflectance is measured from 300 nm to 2 500 nm and sampling interval is 5 nm.

The test specimens shall be measured at the standard conditions, a temperature of $(23 \pm 2) ^\circ\text{C}$ and a relative humidity of $(50 \pm 5) \%$, as specified in ISO 3270. If the alternative conditions are used, it shall be stated in the test report.

5.2 Reference global solar radiation

Reference global solar radiation as defined by the SMARTS 2.9.5 model shall be used. The parameters of reference global solar radiation are: at sea level for air mass, 1,0; aerosol optical depth, 0,10; water vapor, 1,42 atm-cm; ozone, 0,340 atm-cm. The reference global solar radiation from 300 nm to 2 500 nm for 5 nm interval is described in [Annex A](#). If the parameter to calculate reference global solar radiation is different, it shall be reported.

NOTE SMARTS 2.9.5 is a free software. It can be downloaded from the following website: <https://www.nrel.gov/grid/solar-resource/smarts.html>

5.3 Determination of solar reflectance

Solar reflectance is determined by the spectral reflectance of test specimen and the reference global solar radiation using [Formula \(1\)](#):

$$\rho_s = \frac{\int_{\lambda_1}^{\lambda_2} E(\lambda) \cdot \rho(\lambda) d\lambda}{\int_{\lambda_1}^{\lambda_2} E(\lambda) d\lambda} \quad (1)$$

where

ρ_s is the solar reflectance;

$E(\lambda)$ is the reference global solar radiation ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$);

$\rho(\lambda)$ is the spectral reflectance of specimen;

λ is the range of wavelength from λ_1 to λ_2 .

NOTE In case of the wavelength interval is 1 nm instead of 5 nm, the formula becomes as follows:

$$\rho_s = \sum_{\lambda_1}^{\lambda_2} E(\lambda) \cdot \rho(\lambda) / \sum_{\lambda_1}^{\lambda_2} E(\lambda)$$

Example of a determination of solar reflectance is shown in [Annex B](#).

6 Test report

Test report shall include the followings.

- a reference to this document, i.e. ISO 22969:2019;
- a description of test specimen;
- the type of spectrophotometer;
- the reflection measurement geometry;
- the spectral wavelength range and measuring wavelength increments band width and nm-steps used to scan;
- the spectral reflectance of test specimen;
- the solar reflectance;
- any deviation from the test procedure specified;
- any unusual features observed;
- the date of the test.

Annex A (informative)

The reference global radiation table

Reference global solar radiation at sea level for air mass 1,0; aerosol optical depth 0,10; water vapor 1,42 atm-cm; ozone 0,340 atm-cm is described in [Table A.1](#).

Table A.1 — The table of reference global radiation

Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wavelength nm	Irradiance W·m ⁻² ·nm ⁻¹
300	1,48E-02	440	1,72E+00	580	1,66E+00	720	1,14E+00
305	7,65E-02	445	1,83E+00	585	1,66E+00	725	1,15E+00
310	1,89E-01	450	1,93E+00	590	1,57E+00	730	1,16E+00
315	3,11E-01	455	1,94E+00	595	1,59E+00	735	1,24E+00
320	4,24E-01	460	1,96E+00	600	1,59E+00	740	1,24E+00
325	5,70E-01	465	1,94E+00	605	1,60E+00	745	1,26E+00
330	7,22E-01	470	1,91E+00	610	1,59E+00	750	1,25E+00
335	7,10E-01	475	1,93E+00	615	1,55E+00	755	1,23E+00
340	7,56E-01	480	1,95E+00	620	1,55E+00	760	8,01E-01
345	7,48E-01	485	1,82E+00	625	1,51E+00	765	8,25E-01
350	7,93E-01	490	1,84E+00	630	1,50E+00	770	1,14E+00
355	8,21E-01	495	1,87E+00	635	1,52E+00	775	1,17E+00
360	7,79E-01	500	1,82E+00	640	1,51E+00	780	1,16E+00
365	9,43E-01	505	1,82E+00	645	1,49E+00	785	1,14E+00
370	9,90E-01	510	1,80E+00	650	1,47E+00	790	1,11E+00
375	9,24E-01	515	1,71E+00	655	1,40E+00	795	1,10E+00
380	9,70E-01	520	1,71E+00	660	1,42E+00	800	1,09E+00
385	8,45E-01	525	1,75E+00	665	1,43E+00	805	1,08E+00
390	9,89E-01	530	1,78E+00	670	1,45E+00	810	1,06E+00
395	9,29E-01	535	1,77E+00	675	1,45E+00	815	9,46E-01
400	1,40E+00	540	1,74E+00	680	1,42E+00	820	9,21E-01
405	1,53E+00	545	1,75E+00	685	1,35E+00	825	9,43E-01
410	1,56E+00	550	1,75E+00	690	1,26E+00	830	9,48E-01
415	1,63E+00	555	1,74E+00	695	1,32E+00	835	9,80E-01
420	1,62E+00	560	1,69E+00	700	1,33E+00	840	1,00E+00
425	1,59E+00	565	1,68E+00	705	1,34E+00	845	9,98E-01
430	1,44E+00	570	1,65E+00	710	1,35E+00	850	9,55E-01
435	1,61E+00	575	1,66E+00	715	1,28E+00	855	9,21E-01

Table A.1 (continued)

Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wavelength nm	Irradiance W·m ⁻² ·nm ⁻¹
860	9,77E-01	1 035	6,67E-01	1 210	4,31E-01	1 385	4,11E-04
865	9,42E-01	1 040	6,62E-01	1 215	4,43E-01	1 390	1,88E-03
870	9,56E-01	1 045	6,53E-01	1 220	4,48E-01	1 395	1,06E-03
875	9,46E-01	1 050	6,48E-01	1 225	4,46E-01	1 400	3,26E-03
880	9,33E-01	1 055	6,40E-01	1 230	4,50E-01	1 405	4,44E-03
885	9,21E-01	1 060	6,26E-01	1 235	4,51E-01	1 410	8,15E-03
890	9,09E-01	1 065	6,20E-01	1 240	4,48E-01	1 415	2,29E-02
895	8,09E-01	1 070	6,07E-01	1 245	4,44E-01	1 420	2,69E-02
900	6,97E-01	1 075	6,05E-01	1 250	4,40E-01	1 425	4,24E-02
905	7,57E-01	1 080	5,94E-01	1 255	4,32E-01	1 430	5,51E-02
910	6,93E-01	1 085	5,80E-01	1 260	4,17E-01	1 435	4,78E-02
915	6,83E-01	1 090	5,71E-01	1 265	3,91E-01	1 440	5,99E-02
920	7,29E-01	1 095	5,37E-01	1 270	3,80E-01	1 445	7,21E-02
925	7,20E-01	1 100	5,11E-01	1 275	4,07E-01	1 450	8,59E-02
930	5,10E-01	1 105	4,83E-01	1 280	4,00E-01	1 455	1,27E-01
935	2,82E-01	1 110	4,29E-01	1 285	4,05E-01	1 460	1,43E-01
940	4,05E-01	1 115	2,80E-01	1 290	4,06E-01	1 465	1,14E-01
945	3,73E-01	1 120	1,88E-01	1 295	3,97E-01	1 470	8,45E-02
950	3,98E-01	1 125	1,58E-01	1 300	3,79E-01	1 475	1,19E-01
955	4,08E-01	1 130	1,94E-01	1 305	3,61E-01	1 480	1,17E-01
960	4,67E-01	1 135	1,77E-01	1 310	3,44E-01	1 485	1,43E-01
965	5,44E-01	1 140	2,78E-01	1 315	3,22E-01	1 490	1,84E-01
970	6,63E-01	1 145	2,16E-01	1 320	3,06E-01	1 495	2,10E-01
975	6,30E-01	1 150	2,35E-01	1 325	2,94E-01	1 500	2,37E-01
980	6,62E-01	1 155	2,94E-01	1 330	2,29E-01	1 505	2,26E-01
985	7,09E-01	1 160	3,59E-01	1 335	2,18E-01	1 510	2,53E-01
990	7,26E-01	1 165	4,14E-01	1 340	1,97E-01	1 515	2,58E-01
995	7,29E-01	1 170	4,42E-01	1 345	1,15E-01	1 520	2,66E-01
1 000	7,21E-01	1 175	4,38E-01	1 350	2,80E-02	1 525	2,71E-01
1 005	7,00E-01	1 180	4,32E-01	1 355	1,90E-03	1 530	2,70E-01
1 010	7,06E-01	1 185	4,29E-01	1 360	9,10E-05	1 535	2,71E-01
1 015	6,98E-01	1 190	4,39E-01	1 365	7,79E-05	1 540	2,68E-01
1 020	6,88E-01	1 195	4,47E-01	1 370	1,47E-04	1 545	2,70E-01
1 025	6,87E-01	1 200	4,26E-01	1 375	1,59E-03	1 550	2,67E-01
1 030	6,78E-01	1 205	4,26E-01	1 380	1,12E-03	1 555	2,64E-01

Table A.1 (continued)

Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wave-length nm	Irradiance W·m ⁻² ·nm ⁻¹	Wavelength nm	Irradiance W·m ⁻² ·nm ⁻¹
1 560	2,64E-01	1 735	1,65E-01	1 910	2,39E-04	2 085	9,04E-02
1 565	2,61E-01	1 740	1,66E-01	1 915	2,53E-04	2 090	9,25E-02
1 570	2,48E-01	1 745	1,60E-01	1 920	1,82E-03	2 095	9,25E-02
1 575	2,38E-01	1 750	1,67E-01	1 925	3,11E-03	2 100	9,02E-02
1 580	2,41E-01	1 755	1,58E-01	1 930	2,35E-03	2 105	9,44E-02
1 585	2,46E-01	1 760	1,61E-01	1 935	7,91E-03	2 110	9,22E-02
1 590	2,41E-01	1 765	1,41E-01	1 940	7,87E-03	2 115	9,29E-02
1 595	2,48E-01	1 770	1,47E-01	1 945	1,83E-02	2 120	8,97E-02
1 600	2,37E-01	1 775	1,27E-01	1 950	2,49E-02	2 125	9,01E-02
1 605	2,32E-01	1 780	1,12E-01	1 955	1,91E-02	2 130	9,05E-02
1 610	2,28E-01	1 785	9,29E-02	1 960	3,21E-02	2 135	9,07E-02
1 615	2,32E-01	1 790	1,00E-01	1 965	4,28E-02	2 140	9,09E-02
1 620	2,34E-01	1 795	6,12E-02	1 970	6,17E-02	2 145	8,99E-02
1 625	2,37E-01	1 800	4,09E-02	1 975	7,76E-02	2 150	8,65E-02
1 630	2,34E-01	1 805	2,24E-02	1 980	8,30E-02	2 155	8,61E-02
1 635	2,27E-01	1 810	1,74E-02	1 985	8,86E-02	2 160	8,46E-02
1 640	2,16E-01	1 815	7,65E-03	1 990	9,09E-02	2 165	7,88E-02
1 645	2,17E-01	1 820	3,10E-03	1 995	8,66E-02	2 170	8,20E-02
1 650	2,17E-01	1 825	3,84E-03	2 000	5,41E-02	2 175	8,17E-02
1 655	2,19E-01	1 830	2,86E-04	2 005	3,12E-02	2 180	8,23E-02
1 660	2,21E-01	1 835	5,39E-05	2 010	5,36E-02	2 185	7,72E-02
1 665	2,11E-01	1 840	1,08E-05	2 015	4,38E-02	2 190	8,02E-02
1 670	2,12E-01	1 845	1,10E-04	2 020	6,01E-02	2 195	7,96E-02
1 675	2,08E-01	1 850	6,43E-05	2 025	8,26E-02	2 200	7,44E-02
1 680	2,01E-01	1 855	1,73E-05	2 030	9,10E-02	2 205	7,56E-02
1 685	2,04E-01	1 860	1,05E-04	2 035	9,82E-02	2 210	7,89E-02
1 690	2,04E-01	1 865	1,62E-04	2 040	9,52E-02	2 215	7,72E-02
1 695	2,03E-01	1 870	9,74E-06	2 045	9,50E-02	2 220	7,78E-02
1 700	2,00E-01	1 875	3,34E-05	2 050	7,91E-02	2 225	7,62E-02
1 705	1,97E-01	1 880	5,56E-04	2 055	6,93E-02	2 230	7,62E-02
1 710	1,89E-01	1 885	4,56E-04	2 060	7,81E-02	2 235	7,49E-02
1 715	1,89E-01	1 890	1,16E-03	2 065	7,39E-02	2 240	7,40E-02
1 720	1,86E-01	1 895	8,72E-04	2 070	7,68E-02	2 245	7,24E-02
1 725	1,78E-01	1 900	6,48E-05	2 075	8,52E-02	2 250	7,27E-02
1 730	1,75E-01	1 905	2,29E-05	2 080	9,11E-02	2 255	6,99E-02

Table A.1 (continued)

Wave-length nm	Irradiance $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	Wave-length nm	Irradiance $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	Wave-length nm	Irradiance $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	Wavelength nm	Irradiance $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$
2 260	6,91E-02	2 325	5,83E-02	2 390	4,05E-02	2 455	2,91E-02
2 265	6,96E-02	2 330	5,90E-02	2 395	4,38E-02	2 460	3,63E-02
2 270	6,74E-02	2 335	5,91E-02	2 400	4,61E-02	2 465	2,82E-02
2 275	6,66E-02	2 340	5,10E-02	2 405	3,81E-02	2 470	2,13E-02
2 280	6,76E-02	2 345	5,39E-02	2 410	3,75E-02	2 475	2,04E-02
2 285	6,53E-02	2 350	4,65E-02	2 415	3,14E-02	2 480	1,28E-02
2 290	6,50E-02	2 355	5,09E-02	2 420	3,01E-02	2 485	9,36E-03
2 295	6,34E-02	2 360	5,30E-02	2 425	3,68E-02	2 490	6,02E-03
2 300	6,16E-02	2 365	5,12E-02	2 430	4,53E-02	2 495	5,92E-03
2 305	6,19E-02	2 370	3,82E-02	2 435	2,14E-02	2 500	1,14E-02
2 310	6,45E-02	2 375	4,72E-02	2 440	4,32E-02	—	—
2 315	6,05E-02	2 380	4,54E-02	2 445	2,54E-02	—	—
2 320	5,58E-02	2 385	3,67E-02	2 450	1,84E-02	—	—

Annex B (informative)

Example of a determination method of solar reflectance

B.1 Principle of the determination method

The determination method of solar reflectance is described in [Formula \(1\)](#).

[Formula \(1\)](#) can be changed into another formula, using summation expression.

In the case of modified rectangular rule, [Formula \(1\)](#) becomes followings ([B.1](#)):

$$\rho_s = \frac{\sum_{i=1}^{n-1} E(\lambda_i) \cdot \rho(\lambda_i) \cdot d\lambda + \frac{1}{2} [E(\lambda_1) \cdot \rho(\lambda_1) + E(\lambda_n) \cdot \rho(\lambda_n)] \cdot d\lambda}{\sum_{i=1}^{n-1} E(\lambda_i) \cdot d\lambda + \frac{1}{2} [E(\lambda_1) + E(\lambda_n)] \cdot d\lambda} \quad (\text{B.1})$$

where

ρ_s is the solar reflectance;

$E(\lambda_i)$ is the reference global solar radiation ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$) at wavelength λ_i ;

$\rho(\lambda_i)$ is the spectral reflectance of specimen at wavelength λ_i ;

λ_i is the wavelength from λ_1 to λ_n ;

$d\lambda$ is interval of wavelength.

In the case of trapezoid rule, [Formula \(1\)](#) becomes followings ([B.2](#)):

$$\rho_s = \frac{\sum_{i=1}^{n-1} 0,5 \times \{ [E(\lambda_i) \cdot \rho(\lambda_i) + E(\lambda_{i+1}) \cdot \rho(\lambda_{i+1})] \times (\lambda_{i+1} - \lambda_i) \}}{\sum_{i=1}^{n-1} 0,5 \times \{ [E(\lambda_i) + E(\lambda_{i+1})] \times (\lambda_{i+1} - \lambda_i) \}} \quad (\text{B.2})$$

These two formulae are derived from the same solar reflectance.

B.2 Example of calculation

The reference global solar radiation (given in [Annex A](#)) and the spectral reflectance of specimen (grey painted steel specimen) are in [Table B.1](#).

$$\rho_s = 0,318$$

Table B.1 — Example of the reference global solar radiation and the spectral reflectance of specimen

Wavelength nm	$E(\lambda)$ $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	$\rho(\lambda)$	$E(\lambda)\cdot\rho(\lambda)$	Wavelength nm	$E(\lambda)$ $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	$\rho(\lambda)$	$E(\lambda)\cdot\rho(\lambda)$
300	1,48E-02	0,059	8,66E-04	510	1,80E+00	0,375	6,75E-01
305	7,65E-02	0,058	4,46E-03	515	1,71E+00	0,378	6,46E-01
310	1,89E-01	0,058	1,10E-02	520	1,71E+00	0,381	6,51E-01
315	3,11E-01	0,058	1,79E-02	525	1,75E+00	0,383	6,71E-01
320	4,24E-01	0,057	2,42E-02	530	1,78E+00	0,386	6,87E-01
325	5,70E-01	0,056	3,19E-02	535	1,77E+00	0,388	6,87E-01
330	7,22E-01	0,056	4,01E-02	540	1,74E+00	0,390	6,78E-01
335	7,10E-01	0,055	3,92E-02	545	1,75E+00	0,391	6,84E-01
340	7,56E-01	0,055	4,18E-02	550	1,75E+00	0,393	6,87E-01
345	7,48E-01	0,056	4,18E-02	555	1,74E+00	0,394	6,86E-01
350	7,93E-01	0,057	4,54E-02	560	1,69E+00	0,396	6,69E-01
355	8,21E-01	0,060	4,96E-02	565	1,68E+00	0,397	6,66E-01
360	7,79E-01	0,066	5,13E-02	570	1,65E+00	0,398	6,56E-01
365	9,43E-01	0,074	6,93E-02	575	1,66E+00	0,399	6,63E-01
370	9,90E-01	0,084	8,32E-02	580	1,66E+00	0,400	6,64E-01
375	9,24E-01	0,098	9,07E-02	585	1,66E+00	0,400	6,64E-01
380	9,70E-01	0,119	1,16E-01	590	1,57E+00	0,400	6,28E-01
385	8,45E-01	0,149	1,26E-01	595	1,59E+00	0,400	6,36E-01
390	9,89E-01	0,188	1,86E-01	600	1,59E+00	0,399	6,35E-01
395	9,29E-01	0,230	2,14E-01	605	1,60E+00	0,399	6,38E-01
400	1,40E+00	0,268	3,75E-01	610	1,59E+00	0,398	6,32E-01
405	1,53E+00	0,296	4,53E-01	615	1,55E+00	0,396	6,14E-01
410	1,56E+00	0,313	4,88E-01	620	1,55E+00	0,395	6,12E-01
415	1,63E+00	0,322	5,25E-01	625	1,51E+00	0,393	5,94E-01
420	1,62E+00	0,328	5,31E-01	630	1,50E+00	0,392	5,88E-01
425	1,59E+00	0,333	5,29E-01	635	1,52E+00	0,390	5,93E-01
430	1,44E+00	0,338	4,87E-01	640	1,51E+00	0,389	5,87E-01
435	1,61E+00	0,344	5,54E-01	645	1,49E+00	0,387	5,77E-01
440	1,72E+00	0,351	6,03E-01	650	1,47E+00	0,386	5,68E-01
445	1,83E+00	0,355	6,49E-01	655	1,40E+00	0,385	5,39E-01
450	1,93E+00	0,358	6,90E-01	660	1,42E+00	0,384	5,46E-01
455	1,94E+00	0,359	6,96E-01	665	1,43E+00	0,383	5,48E-01
460	1,96E+00	0,360	7,05E-01	670	1,45E+00	0,382	5,54E-01
465	1,94E+00	0,360	6,98E-01	675	1,45E+00	0,381	5,52E-01
470	1,91E+00	0,360	6,87E-01	680	1,42E+00	0,379	5,38E-01
475	1,93E+00	0,360	6,95E-01	685	1,35E+00	0,377	5,09E-01
480	1,95E+00	0,361	7,03E-01	690	1,26E+00	0,376	4,74E-01
485	1,82E+00	0,361	6,58E-01	695	1,32E+00	0,375	4,95E-01
490	1,84E+00	0,363	6,68E-01	700	1,33E+00	0,374	4,98E-01
495	1,87E+00	0,365	6,83E-01	705	1,34E+00	0,373	5,00E-01
500	1,82E+00	0,368	6,70E-01	710	1,35E+00	0,372	5,02E-01
505	1,82E+00	0,371	6,76E-01	715	1,28E+00	0,371	4,74E-01

Table B.1 (continued)

Wavelength nm	$E(\lambda)$ $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	$\rho(\lambda)$	$E(\lambda)\cdot\rho(\lambda)$	Wavelength nm	$E(\lambda)$ $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	$\rho(\lambda)$	$E(\lambda)\cdot\rho(\lambda)$
720	1,14E+00	0,369	4,21E-01	945	3,73E-01	0,317	1,18E-01
725	1,15E+00	0,369	4,24E-01	950	3,98E-01	0,316	1,26E-01
730	1,16E+00	0,367	4,26E-01	955	4,08E-01	0,315	1,28E-01
735	1,24E+00	0,366	4,54E-01	960	4,67E-01	0,314	1,46E-01
740	1,24E+00	0,364	4,51E-01	965	5,44E-01	0,313	1,70E-01
745	1,26E+00	0,362	4,56E-01	970	6,63E-01	0,312	2,07E-01
750	1,25E+00	0,360	4,50E-01	975	6,30E-01	0,311	1,96E-01
755	1,23E+00	0,359	4,41E-01	980	6,62E-01	0,310	2,05E-01
760	8,01E-01	0,357	2,86E-01	985	7,09E-01	0,309	2,19E-01
765	8,25E-01	0,356	2,94E-01	990	7,26E-01	0,308	2,24E-01
770	1,14E+00	0,356	4,05E-01	995	7,29E-01	0,307	2,24E-01
775	1,17E+00	0,356	4,16E-01	1 000	7,21E-01	0,306	2,21E-01
780	1,16E+00	0,355	4,11E-01	1 005	7,00E-01	0,305	2,14E-01
785	1,14E+00	0,353	4,03E-01	1 010	7,06E-01	0,304	2,15E-01
790	1,11E+00	0,352	3,90E-01	1 015	6,98E-01	0,303	2,12E-01
795	1,10E+00	0,350	3,85E-01	1 020	6,88E-01	0,303	2,08E-01
800	1,09E+00	0,350	3,81E-01	1 025	6,87E-01	0,302	2,07E-01
805	1,08E+00	0,349	3,76E-01	1 030	6,78E-01	0,301	2,04E-01
810	1,06E+00	0,347	3,68E-01	1 035	6,67E-01	0,300	2,00E-01
815	9,46E-01	0,345	3,26E-01	1 040	6,62E-01	0,299	1,98E-01
820	9,21E-01	0,343	3,16E-01	1 045	6,53E-01	0,298	1,95E-01
825	9,43E-01	0,342	3,23E-01	1 050	6,48E-01	0,297	1,93E-01
830	9,48E-01	0,342	3,24E-01	1 055	6,40E-01	0,297	1,90E-01
835	9,80E-01	0,341	3,34E-01	1 060	6,26E-01	0,296	1,85E-01
840	1,00E+00	0,340	3,40E-01	1 065	6,20E-01	0,295	1,83E-01
845	9,98E-01	0,338	3,37E-01	1 070	6,07E-01	0,294	1,78E-01
850	9,55E-01	0,337	3,22E-01	1 075	6,05E-01	0,293	1,77E-01
855	9,21E-01	0,336	3,09E-01	1 080	5,94E-01	0,292	1,74E-01
860	9,77E-01	0,335	3,27E-01	1 085	5,80E-01	0,292	1,69E-01
865	9,42E-01	0,334	3,14E-01	1 090	5,71E-01	0,291	1,66E-01
870	9,56E-01	0,333	3,18E-01	1 095	5,37E-01	0,290	1,56E-01
875	9,46E-01	0,332	3,14E-01	1 100	5,11E-01	0,289	1,48E-01
880	9,33E-01	0,330	3,08E-01	1 105	4,83E-01	0,288	1,39E-01
885	9,21E-01	0,329	3,03E-01	1 110	4,29E-01	0,288	1,23E-01
890	9,09E-01	0,327	2,97E-01	1 115	2,80E-01	0,287	8,02E-02
895	8,09E-01	0,326	2,63E-01	1 120	1,88E-01	0,286	5,37E-02
900	6,97E-01	0,325	2,26E-01	1 125	1,58E-01	0,285	4,50E-02
905	7,57E-01	0,324	2,45E-01	1 130	1,94E-01	0,284	5,51E-02
910	6,93E-01	0,322	2,23E-01	1 135	1,77E-01	0,283	5,01E-02
915	6,83E-01	0,322	2,20E-01	1 140	2,78E-01	0,282	7,85E-02
920	7,29E-01	0,321	2,34E-01	1 145	2,16E-01	0,281	6,08E-02
925	7,20E-01	0,320	2,30E-01	1 150	2,35E-01	0,280	6,59E-02
930	5,10E-01	0,319	1,63E-01	1 155	2,94E-01	0,280	8,22E-02
935	2,82E-01	0,318	8,98E-02	1 160	3,59E-01	0,279	1,00E-01
940	4,05E-01	0,318	1,29E-01	1 165	4,14E-01	0,278	1,15E-01

Table B.1 (continued)

Wavelength nm	$E(\lambda)$ $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	$\rho(\lambda)$	$E(\lambda)\cdot\rho(\lambda)$	Wavelength nm	$E(\lambda)$ $\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$	$\rho(\lambda)$	$E(\lambda)\cdot\rho(\lambda)$
1 170	4,42E-01	0,277	1,22E-01	1 395	1,06E-03	0,242	2,56E-04
1 175	4,38E-01	0,276	1,21E-01	1 400	3,26E-03	0,241	7,86E-04
1 180	4,32E-01	0,275	1,19E-01	1 405	4,44E-03	0,240	1,07E-03
1 185	4,29E-01	0,274	1,18E-01	1 410	8,15E-03	0,239	1,95E-03
1 190	4,39E-01	0,273	1,20E-01	1 415	2,29E-02	0,238	5,46E-03
1 195	4,47E-01	0,272	1,22E-01	1 420	2,69E-02	0,237	6,39E-03
1 200	4,26E-01	0,272	1,16E-01	1 425	4,24E-02	0,237	1,00E-02
1 205	4,26E-01	0,271	1,15E-01	1 430	5,51E-02	0,236	1,30E-02
1 210	4,31E-01	0,270	1,16E-01	1 435	4,78E-02	0,235	1,12E-02
1 215	4,43E-01	0,269	1,19E-01	1 440	5,99E-02	0,234	1,40E-02
1 220	4,48E-01	0,269	1,20E-01	1 445	7,21E-02	0,233	1,68E-02
1 225	4,46E-01	0,268	1,19E-01	1 450	8,59E-02	0,233	2,00E-02
1 230	4,50E-01	0,267	1,20E-01	1 455	1,27E-01	0,232	2,95E-02
1 235	4,51E-01	0,267	1,20E-01	1 460	1,43E-01	0,231	3,30E-02
1 240	4,48E-01	0,266	1,19E-01	1 465	1,14E-01	0,230	2,63E-02
1 245	4,44E-01	0,265	1,18E-01	1 470	8,45E-02	0,230	1,94E-02
1 250	4,40E-01	0,265	1,16E-01	1 475	1,19E-01	0,229	2,72E-02
1 255	4,32E-01	0,264	1,14E-01	1 480	1,17E-01	0,228	2,67E-02
1 260	4,17E-01	0,263	1,10E-01	1 485	1,43E-01	0,227	3,25E-02
1 265	3,91E-01	0,262	1,03E-01	1 490	1,84E-01	0,227	4,17E-02
1 270	3,80E-01	0,262	9,94E-02	1 495	2,10E-01	0,226	4,75E-02
1 275	4,07E-01	0,261	1,06E-01	1 500	2,37E-01	0,226	5,34E-02
1 280	4,00E-01	0,260	1,04E-01	1 505	2,26E-01	0,225	5,08E-02
1 285	4,05E-01	0,259	1,05E-01	1 510	2,53E-01	0,224	5,67E-02
1 290	4,06E-01	0,259	1,05E-01	1 515	2,58E-01	0,223	5,76E-02
1 295	3,97E-01	0,258	1,02E-01	1 520	2,66E-01	0,223	5,92E-02
1 300	3,79E-01	0,257	9,74E-02	1 525	2,71E-01	0,222	6,02E-02
1 305	3,61E-01	0,256	9,25E-02	1 530	2,70E-01	0,222	5,98E-02
1 310	3,44E-01	0,255	8,79E-02	1 535	2,71E-01	0,221	5,99E-02
1 315	3,22E-01	0,255	8,20E-02	1 540	2,68E-01	0,220	5,90E-02
1 320	3,06E-01	0,254	7,77E-02	1 545	2,70E-01	0,220	5,93E-02
1 325	2,94E-01	0,253	7,44E-02	1 550	2,67E-01	0,219	5,84E-02
1 330	2,29E-01	0,252	5,77E-02	1 555	2,64E-01	0,218	5,75E-02
1 335	2,18E-01	0,251	5,48E-02	1 560	2,64E-01	0,217	5,74E-02
1 340	1,97E-01	0,251	4,94E-02	1 565	2,61E-01	0,217	5,65E-02
1 345	1,15E-01	0,250	2,87E-02	1 570	2,48E-01	0,216	5,35E-02
1 350	2,80E-02	0,249	6,97E-03	1 575	2,38E-01	0,215	5,12E-02
1 355	1,90E-03	0,248	4,72E-04	1 580	2,41E-01	0,214	5,17E-02
1 360	9,10E-05	0,247	2,25E-05	1 585	2,46E-01	0,214	5,26E-02
1 365	7,79E-05	0,246	1,92E-05	1 590	2,41E-01	0,213	5,13E-02
1 370	1,47E-04	0,246	3,61E-05	1 595	2,48E-01	0,213	5,27E-02
1 375	1,59E-03	0,245	3,89E-04	1 600	2,37E-01	0,212	5,02E-02
1 380	1,12E-03	0,244	2,73E-04	1 605	2,32E-01	0,211	4,90E-02
1 385	4,11E-04	0,243	1,00E-04	1 610	2,28E-01	0,210	4,79E-02
1 390	1,88E-03	0,243	4,56E-04	1 615	2,32E-01	0,210	4,86E-02