consider Datents. ctice, and no comic investigate or cinfingment of g il reports, weluding standards approved and practices reco is no agreement to adhere to any SAE standard or recomm approving technical reports, the Board and its Committee report are responsible for protecting themselves against the SAE Technical Board rules provides that: "All technical e engaged in industry or trade is entitlely voluntary. There is or be guided by any technical report. In formulating and a may apply to the subject matter. Prospective users of the Section 7C of the use by anyone ento conform to o patents which m

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc. 29 West 39th Street New York City AMS 3286A

Issued 6-1-42 Revised 12-1-53

FELT, FIRM PAD, WHITE 100% Wool

- 1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase order.
- 2. APPLICATION: Primarily for oil and grease retention where the felt is confined and compressed in assembly. Also suitable for dust shields where conditions are not severe.
- MATERIAL AND FABRICATION: Material shall be made from white wool fibers built up by a suitable combination of mechanical work, chemical action, moisture and heat, without spinning, weaving or knitting, to produce a uniform, well felted product.
- 4. TECHNICAL REQUIREMENTS:
- 4.1 General:
- 4.1.1 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
- 1.2 Properties: The product shall conform to the following requirements; tests shall be conducted on the product supplied and in accordance with ASTM Du61-51, insofar as practicable.

225

և.2.1	Tensile Strength, psi, min	22)
4.2.2	Splitting Resistance, 1b per 2 in. width, min	8
1.2.3	Actual wool content, %, min	95
4.2.4	Carbon tetrachloride soluble, %, max	2.5
4.2.5	Water soluble, %, max	2.5
4.2. 6	Carbon tetrachloride soluble + water soluble, total, %, max	3.0
ø 4.2.7	Ash, %, max	2.5

AMS 3286 A

4.2.8 Weight, 1b per sq yd

ø	Nominal Thickness Inch	Min	Max	Nominal Thickness Inch	Min	Max
	1/8	0.98	1.14	1/2	3.92	14.56
	3/16	1.47	1.71	5/8	4.90	5.70
	1/4	1.96	2.28	3/l _i	5.88	6.81
	5/16	2.45	2.85	7/8	6.86	7.98
	3/8	2.94	3.42	1	7.84	9.12

- 5. QUALITY: The product shall be uniform in thickness and shall be free from tears, holes, lumps, wrinkles, and foreign materials and from defects detrimental to fabrication, appearance or performance of parts.
- 6. TOLERANCES: Unless otherwise specified, the following tolerances apply:

	Nominal Thickness	Thickness	Tolerance, Inch
ø	Inch	Plus	Minus
	7 /8	0.105	0.145
	3/16	0.165	0.211
	ı̃/L̄	0.224	0.276
	5/16	0.281	0.342
	3/8	0.313	0.407
	1/2	0.462	0.538
	5/8	0.581	0.669
	3/4	0.700	0.800
	7/8	0.819	0.931
	í	0.938	1.062

7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product meets the requirements of this specification. This report shall include the purchase order number, material specification number, vendor's compound number, thickness, size and quantity.
- 7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
- B. IDENTIFICATION: Containers shall be marked with AMS 3286A, purchase order number, part number, and quantity. Pieces of different part numbers shall not be packed in the same container.