

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

AMS 3892/1A

Issued 11-15-72
Revised 7-1-84

TOW OR YARN, CARBON (GRAPHITE) FIBERS For Structural Composites

GF 400 (2760) Tensile Strength, 33 (228) Tensile Modulus

1. SCOPE:

1.1 **Form:** This specification covers one type of continuous multifilament carbon (graphite) fibers in the form of a tow or yarn (when twisted). The weight per unit length of the tow or yarn is governed by the filament count which is identified by the supplier's grade or material designation.

1.2 **Classification:** Carbon (graphite) tow or yarn, derived from a polyacrylonitrile precursor, with typical 400,000 psi (2760 MPa) tensile strength and 33,000,000 psi (228 GPa) tensile modulus for use in general purpose structural composites requiring high tensile strength and moderate modulus of elasticity in tension.

2. **APPLICABLE DOCUMENTS:** See AMS 3892.

3. TECHNICAL REQUIREMENTS:

3.1 **Basic Specification:** The complete requirements for procuring the carbon (graphite) tow or yarn described herein shall consist of this document and the latest issue of the basic specification, AMS 3892.

3.2 **Storage Life:** The product shall meet the interlaminar shear strength requirements of this specification when tested at any time up to 6 months from date of receipt by purchaser provided it has been stored at room temperature in the original closed container.

3.3 **Properties:** Shall be as follows; the requirements of 3.3.1, 3.3.2, and 3.3.4 apply to the average of the number of determinations indicated in the basic specification but no individual value shall be less than 90% of the specified minimum average unless due to an obvious testing problem, in which case a substitute specimen may be tested.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

REAFFIRMED