

AEROSPACE MATERIAL SPECIFICATION



AMS 4006J

Issued
Revised

NOV 1941
AUG 2005

Superseding AMS 4006H

Aluminum Alloy, Sheet and Plate
1.25Mn - 0.12Cu (3003-0)
Annealed

(Composition similar to UNS A93003)

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application:

This product has been used typically for parts fabricated by spinning or severe forming where good weldability is required, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials
AS1990	Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2005 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
http://www.sae.org

SAE WEB ADDRESS:

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
 ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Publications:

Available from ANSI, 25 West 43rd Street, 4th Floor, New York, NY 10036 or www.ansi.org.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
 ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355.

TABLE 1 - Composition

Element	min	max
Silicon	--	0.6
Iron	--	0.7
Copper	0.05	0.20
Manganese	1.0	1.5
Zinc	--	0.10
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Annealed in accordance with AMS 2772 to the T-0 temper (See AS1990).

3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 on the mill produced size.

3.3.1 Tensile Properties: Shall be as specified in Table 2.

TABLE 2A - Tensile Properties, Inch/Pound Units

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi, minimum	Elongation in 2 Inches or 4D %, minimum
0.006 to 0.007, incl	14.0 to 19.0	5.0	14
Over 0.007 to 0.012, incl	14.0 to 19.0	5.0	18
Over 0.012 to 0.031, incl	14.0 to 19.0	5.0	20
Over 0.031 to 0.050, incl	14.0 to 19.0	5.0	23
Over 0.050 to 0.249, incl	14.0 to 19.0	5.0	25
Over 0.249 to 3.000, incl	14.0 to 19.0	5.0	23

TABLE 2B - Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa, minimum	Elongation in 50.8 mm or 4D %, minimum
0.15 to 0.18, incl	97 to 131	34.5	14
Over 0.18 to 0.30, incl	97 to 131	34.5	18
Over 0.30 to 0.79, incl	97 to 131	34.5	20
Over 0.79 to 1.27, incl	97 to 131	34.5	23
Over 1.27 to 6.32, incl	97 to 131	34.5	25
Over 6.32 to 76.20, incl	97 to 131	34.5	23

3.3.2 Bending: Product 0.249 inch (6.32 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each lot.

4.2.2 Periodic Tests: Bending (3.3.2) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS 4006J, size, and quantity. The report shall also identify the producer, the product form, and size of the mill product.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

Shall be in accordance with ASTM B 666/B 666M.

5.2 Packaging:

5.2.1 Flat sheet, plate, and circles shall be protected from damage during storage and shipment by a method determined by vendor unless specified by purchaser. Examples of typical protective methods include but are not limited to interleaving with paper or oiling of the surface.