# AEROSPACE MATERIAL SPECIFICATIONS

AMS 4012A

1-15-58 Revised 6-30-62

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

ALUMINUM SHEET, LAMINATED, EDGE BONDED

- 1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. APPLICATION: Primarily for shims of special shapes in which thickness is to be adjusted by removal of laminations as required.
- 3. COMPOSITION:
- 3.1 Laminations: Shall be 1100, 1145, 3003, or 5052 aluminum alloy foil. Unless otherwise specified, the choice of alloy shall be at the discretion of the producer.
- 3.2 Solid Base: Shall be AMS 4041 aluminum alloy sheet.
- 3.3 Adhesive: Shall be of a composition which will meet the fabrication and quality requirements of this specification.
- 4. FABRICATION:
- 4.1 The product shall be fabricated from hard or extra hard laminations, in combination with a solid base when required, precut to the desired shape, stacked
- to the desired thickness, and then bonded completely around all edges with adhesive. Laminations shall be 0.003 in. + 0.0003 thick unless 0.002 in. + 0.0002 laminations are specified or required to produce the nominal laminate thickness.
- 4.2 Unless otherwise specified, the product shall be available in the following thicknesses and combinations of laminations and solid base:

Nominal Thickness		Half Solid	Three Quarters Solid
Inch	All Laminations	Half Laminations	One Quarter Laminations
A			
0.006	X		
0.008	X		
0.010	X		
0.016	X		
0.020	X		
0.032	X		
0.047	X		
0.062	X	. <b>X</b>	
0.094	X	X	
0.125	X	X	X
0.190	X	X	<b>x</b>

## AMS 4012A

### 5. QUALITY:

- 5.1 Material shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
- 5.2 Laminations shall be bonded together in such a manner that normal handling shall not cause separation. The layers shall be capable of being readily peeled.
- 6. TOLERANCES: The maximum taper in thickness for panels 2 in. or less in length shall be 0.002 inch. For parts over 2 in. in length, the maximum taper shall be 0.002 in. plus 0.0005 in. for each inch of length over 2 inches. Unless otherwise specified, thickness tolerances shall be as specified below:

hickness	Tolerance, Inch Plus Only
	0.001
	<b>9.</b> 002
incl	0.004
incl	0.006
	0.008
incl	0.010
	<pre>incl incl incl incl</pre>

### 7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for composition or stating that the chemical composition of the shim stock conforms to the requirements specified. This report shall include the purchase order number, material specification number, shim stock thickness, foil thickness, size, and quantity.
- 7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

#### 8. IDENTIFICATION:

- 8.1 Laminated shim stock shall be marked with nominal shim stock thickness, nominal
- foil thickness, percentage of total thickness which is laminated, nominal thickness of solid base if present, and AMS 4012.
- 8.2 Packages of laminated shim stock shall be marked with the purchase order number,
- AMS 4012, nominal shim stock thickness, nominal foil thickness, size, and
  quantity.
- 8.3 Packages of parts shall be marked with part number, purchase order number, and quantity.