



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

AMS 4156D

Superseding AMS 4156C

Issued 11-1-49

Revised 9-30-66

ALUMINUM ALLOY EXTRUSIONS

0.65Mg - 0.40Si (6063-T6)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Bars, rods, wire, shapes, and tubing.
3. **APPLICATION:** Primarily for hinges, trim strips, window frames, sills, and moldings where good surface finish is required. Also may be used to advantage for hollow, partially enclosed, and intricate shapes for which an alloy having good extruding characteristics is required.
4. **COMPOSITION:**

	min	max
Magnesium	0.45	0.9
Silicon	0.20	0.6
Iron	--	0.35
Chromium	--	0.10
Manganese	--	0.10
Titanium	--	0.10
Copper	--	0.10
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

5. **CONDITION:** Solution and precipitation heat treated.
- 5.1 Unless otherwise specified, extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within the dimensional tolerances.
6. **TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.

6.1 Tensile Properties:

Nominal Diameter or Least Thickness (rods, bars, shapes) or Nominal Wall Thickness (tubing) Inch	Tensile Strength psi, min	Yield Strength at 0. 2% Offset or at Extension Indicated (E = 9, 900, 000)		Elongation % in 2 in. or 4D, min
		Extension Under Load		
		psi, min	in. in 2 in.	
Up to 0. 125, excl	30, 000	25, 000	0. 0091	8
0. 125 to 1. 000, incl	30, 000	25, 000	0. 0091	10

- 6.1.1 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

SAE Technical Board rules provide that: "All technical reports, including standards, specifications, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."