

STEEL BARS, FORGINGS, AND TUBING
0.50Cr - 0.55Ni - 0.20Mo (0.18 - 0.23C) (SAE 8620)
Vacuum Arc or Electroslag Remelted

UNS G86200

1. SCOPE:

- 1.1 Form: This specification covers a premium aircraft-quality, low-alloy steel in the form of bars, forgings, mechanical tubing, and forging stock.
- 1.2 Application: Primarily for carburized parts requiring high minimum core hardness in sections 0.375 inch (9.52 mm) and under in nominal thickness, and which are subject to rigid magnetic particle standards. The core may or may not be machinable after hardening.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Standards shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.1 Aerospace Material Specifications:

- AMS 2251 - Tolerances, Low-Alloy Steel Bars
- MAM 2251 - Tolerances, Metric, Low-Alloy Steel Bars
- AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
- MAM 2253 - Tolerances, Metric, Carbon and Alloy Steel Tubing
- AMS 2259 - Chemical Check Analysis Limits, wrought Low-Alloy and Carbon Steels
- AMS 2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
- MAM 2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
- AMS 2350 - Standards and Test Methods
- AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
- AMS 2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
- AMS 2375 - Control of Forgings Requiring First Article Approval
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings

2.1.2 Aerospace Standards:

- AS 1182 - Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A255 - End-Quench Test for Hardenability of Steels
- ASTM A370 - Mechanical Testing of Steel Products
- ASTM A604 - Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
- ASTM E112 - Determining Average Grain Size
- ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

- MIL-STD-163 - Steel Mill Products - Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.18	0.23
Manganese	0.70	1.00
Silicon	0.15	0.35
Phosphorus	--	0.012
Sulfur	--	0.010
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.15	0.25
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition: The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A370:

3.2.1 Bars:

3.2.1.1 Bars 0.500 Inch (12.70 mm) and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished having tensile strength not higher than 125,000 psi (862 MPa).

3.2.1.2 Bars Over 0.500 Inch (12.70 mm) in Nominal Diameter or Distance Between Parallel Sides: Hot finished and annealed having hardness not higher than 229 HB, or equivalent, except that bars ordered cold finished may have hardness as high as 248 HB, or equivalent.

3.2.2 Forgings: As ordered.

3.2.3 Mechanical Tubing: Cold finished having hardness not higher than 25 HRC, or equivalent, except that tubing ordered hot finished and annealed shall have hardness not higher than 99 HRB, or equivalent.

3.2.4 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties: The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A370:

3.3.1 Macrostructure: Visual examination of transverse sections as in 4.3.3 from bars, billets, tube rounds or tubes, and forging stock, rings, etched in accordance with ASTM A604 in hot hydrochloric acid (1:1) at 160° - 180°F (71° - 82°C) for sufficient time to develop a well-defined macrostructure, shall show no pipe or cracks. Except as specified in 3.3.1.1, porosity, segregation, inclusions, and other imperfections for product 36 square inches (232 cm²) and under in cross-sectional area shall be no worse than the following macrographs of ASTM A604; macrostructure standards for product over 36 square inches (232 cm²) in cross-sectional area shall be as agreed upon by purchaser and vendor:

Class	Condition	Severity
1	Freckles	A
2	White spots	A
3	Radial segregation	B
4	Ring pattern	B

3.3.1.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.

3.3.2 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, determined in accordance with ASTM E112.

3.3.3 Hardenability: Shall be J48=1 maximum and J32=3 minimum, determined on the standard end-quench test specimen in accordance with ASTM A255 except that the steel shall be normalized at 1700°F + 10 (927°C + 5) and the test specimen austenitized at 1550°F + 10 (843°C + 5). The hardenability test is not required on a product which will not yield a suitable specimen but the steel from which the product is made shall conform to the hardenability specified.

3.4 Quality:

3.4.1 Steel shall be premium aircraft quality conforming to AMS 2300 or MAM 2300; it shall be multiple melted using either vacuum or electroslag remelt practice in the remelt cycle.

3.4.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to its use.

3.4.2.1 Bars and tubing ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

- 3.4.2.2 Product ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other imperfections exposed to the machined surfaces. Standard machining allowance shall be in accordance with AS 1182.
- 3.4.3 Grain flow of die forgings, except in areas which contain flash line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 - 20 feet (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).
- 3.6 Tolerances: Shall conform to all applicable requirements of the following:
- 3.6.1 Bars: AMS 2251 or MAM 2251.
- 3.6.2 Mechanical Tubing: AMS 2253 or MAM 2253.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.2.2 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a forging to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.
- 4.2.2.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling: Shall be in accordance with the following; a heat shall be the
∅ consumable electrode remelted ingots from steel originally melted as a single furnace charge:

4.3.1 Bars and Mechanical Tubing: AMS 2370.

4.3.2 Forgings and Forging Stock: AMS 2372.

4.3.3 Samples for macrostructure (3.3.1) rating shall be full cross-sectional
∅ specimens obtained from the finished billet or suitable rerolled product representing the top and bottom of at least the first, middle, and last usable ingot from each heat. When ingot location is not available, the lot shall be sampled at one end of at least 10% of the billets or bars.

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of bars, forgings, and mechanical tubing shall furnish with each shipment a report showing the results of tests for chemical composition, macrostructure, grain size, hardenability, and frequency-severity cleanliness rating of each heat. This report shall include the purchase order number, heat number, AMS 6277D, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5.2 The vendor of forging stock shall furnish with each shipment a report
∅ showing the results of tests for chemical composition and frequency-severity cleanliness rating of each heat. This report shall include the purchase order number, heat number, AMS 6277D, size, and quantity.

4.5.3 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 6277D, contractor or other direct supplier of product, part number, and quantity. When product for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of product to determine conformance to the requirements of this specification and shall include in the report either a statement that the product conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.6 Resampling and Retesting: Shall be in accordance with the following:

4.6.1 Bars and Mechanical Tubing: AMS 2370.

4.6.2 Forgings and Forging Stock: AMS 2372.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Shall be as follows:

5.1.1 Bars and Mechanical Tubing: In accordance with AMS 2806.